

Corecell™ S-Foam

Structural Foam Core

- High hydrostatic crush strength and water resistance
- Outstanding mechanical properties
- Ultra-fine cell size
- Lower density than resin-based syntactics

Introduction

Corecell S-Foam shares the benefits of SAN chemistry common to all Corecell products.

Built in toughness – High ductility and damage tolerance

Fine cell size – Resin absorption is very low, saving both weight and cost

Superior uniformity – More consistent density than resin-based syntactics

Eliminating outgassing – Corecell eliminates the problems of foam outgassing

Compatibility – Suitable for use with all polyester, vinylester and epoxy resins

No inhibition - Corecell does not inhibit any epoxy resin curing mechanisms

Handling – Robust for easy machining and use

Corecell S-Foam has been designed specifically for use in sub-sea buoyancy applications. Its resistance to crushing means that it can withstand depths of over 1300m, and its closed-cell structure gives it a high water resistance that ensures buoyancy is maintained over time. With its very high compressive strength, Corecell S-Foam can also replace other materials, such as plywood, when creating high strength inserts for through-bolting in composite laminates.

Having the smallest cell size of all the Corecell products, Corecell S-Foam absorbs very little resin in lamination processes, thus minimising weight gain. The small cell size and the product's inherent toughness also contribute to the excellent machineability of Corecell S-Foam. Complex shapes can be created in Corecell S-Foam using a variety of milling, routing, sawing and drilling techniques.

Corecell S-Foam is available at lower densities that can be achieved with a syntactic, with standard products ranging from 150 to just over 300kg/m³.



Type	Test Method	Units	S800	S1200	S1800
Average Density	ASTM D1622	kg/m ³	150	210	315
Manufacturing Range		kg/m ³	140-160	200-220	300-330
Average Density		lb/ft ³	9.3	13.1	19.7
Manufacturing Range		lb/ft ³	8.7-10.0	12.5-13.7	18.7-20.5
Hydrostatic Crush Pressure (HCP)*	ASTM D-2736	Bar	>20	>45	>90
		Mean MPa	3.46	6.19	10.97
		Mean psi	500	900	1,590
		m of Water	353	632	1119
Compression Strength	ASTM D1621 or DIN 53421	Mean MPa	2.79	4.71	9.17
		Mean psi	405	683	1,331
Compressive Modulus	ASTM D1621b or DIN 53421	Mean MPa	224	359	634
		Mean psi	32,530	52,140	92,040
Shear Strength	ISO 1922	Mean MPa	1.85	2.91	5.21
		Mean psi	268	422	756
Shear Modulus	ISO 1922	Mean MPa	64.8	98.4	157
		Mean psi	9,400	14,270	22,800
Shear Elongation	ISO 1922	Mean %	16%	13%	9%
Dimensional Stability**	DIN 53424	°C	100	100	110
Thermal Conductivity	ASTM C518	W/mK	0.04	0.05	0.06

* This is where at a pressure of 1-2 bar per second, the material has lost 5% of its volume, when loaded for 1 minute

** at elevated temperature with flexural load

Notice

SP is a technology brand of Gurit AG (the company). All advice, instruction or recommendation is given in good faith but the Company only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at the Company's Website: www.gurit.com/termsandconditions_en.html.

The Company strongly recommends that Customers make test panels and conduct appropriate testing of any goods or materials supplied by the Company to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

Gurit are continuously reviewing and updating literature. Please ensure that you have the current version, by contacting Gurit Marketing Communications or your sales contact and quoting the revision number in the bottom left-hand corner of this page.

Gurit (UK) Ltd

St Cross Business Park
Newport, Isle of Wight
United Kingdom PO30 5WU

T +44 (0) 1983 828 000
F +44 (0) 1983 828 100
E marine@gurit.com
W www.gurit.com

Gurit (Australia) Pty Ltd

Unit 1A / 81 Bassett Street,
Mona Vale, 2103 NSW,
Australia

T +61 (0) 2 9979 7248
F +61 (0) 2 9979 6378
E sales-au@gurit.com
W www.gurit.com

Gurit (Canada) Inc

175 rue Péladeau,
Magog, (Québec)
J1X 5G9, Canada

T +1 819 847 2182
F +1 819 847 2572
E info-na@gurit.com
W www.gurit.com